

令和 8 年 2 月度

殿

株式会社 日栄商事
岐阜県羽島市江吉良町江中7-16

項目 種類	外 観 及 び 形 状	寸 法 及 び 許 容 差 mm									圧縮強さ N			開孔率 %		
		a			b			d			JIS規格値		測定値		a	
		JIS規格値	測定値		JIS規格値	測定値		JIS規格値	測定値				最大	最小		
			最大	最小		最大	最小		最大	最小	最大	最小				
20-3.2	良	7.0以上	8.2	8.1	2.0以上	2.6	2.5	±1.0	19.7	19.5	35以上	201	187	30以上	42	
20-4	良		8.2	8.1		2.6	2.5		19.7	19.5	40以上	207	196		42	
●25-2.9	良		8.1	8.0		2.6	2.5		24.3	24.2	◆35以上	141	129		38	
25-3.2	良		8.1	8.0		2.6	2.5		24.3	24.1	35以上	141	128		38	
25-4	良		8.1	8.0		2.6	2.5		24.3	24.1	40以上	138	130		38	
25-5	良		8.1	8.0		2.6	2.5		24.2	24.1	49以上	139	129		38	
25-6/D6	良		8.1	8.0		2.6	2.5		24.3	24.1	54以上	137	128		36	
●30-2.9	良		8.2	8.1		2.6	2.5		29.8	29.7	◆35以上	138	128		39	
30-3.2	良		8.2	8.1		2.7	2.6		29.9	29.7	35以上	138	129		39	
30-4	良		8.2	8.1		2.7	2.6		29.9	29.6	40以上	142	128		38	
30-5	良		8.2	8.1		2.7	2.6		29.8	29.7	49以上	137	128		37	
30-6/D6	良		8.2	8.1		2.7	2.6		29.9	29.6	54以上	142	128		36	
35-3.2	良		8.2	8.1		2.8	2.7		34.5	34.3	35以上	141	130		48	
35-4	良		8.2	8.1		2.8	2.7		34.4	34.2	40以上	138	127		48	
35-5	良		8.2	8.1		2.8	2.7		34.4	34.2	49以上	139	129		46	
35-6/D6	良		8.2	8.1		2.8	2.7		34.4	34.3	54以上	141	128		46	
※35-D10	良		9.1	8.9		2.9	2.8		34.8	34.7	59以上	186	176		34	
40-3.2	良	8.0以上	9.1	9.1	2.5以上	3.1	3.0	±2.0	39.6	39.4	35以上	160	151	35以上	47	
40-4	良		9.2	9.1		3.1	3.0		39.5	39.4	40以上	157	149		47	
40-5	良		9.1	9.0		3.1	3.0		39.6	39.4	49以上	160	149		46	
40-6/D6	良		9.1	9.0		3.1	3.0		39.6	39.5	54以上	159	148		45	
40-D10	良		10.0	10.0		3.1	3.0		39.6	39.5	59以上	230	221		43	
40-D13	良		10.1	10.0		3.2	3.1		39.7	39.5	79以上	233	222		41	
45-3.2	良		10.2	10.1		3.5	3.4		45.2	45.0	35以上	206	196		48	
45-4	良		10.2	10.1		3.5	3.4		45.1	44.9	40以上	202	192		48	
45-5	良		10.1	10.0		3.5	3.4		45.2	45.0	49以上	199	187		47	
45-6/D6	良		10.0	9.9		3.5	3.4		45.0	44.8	54以上	200	185		47	
※45-D10	良		14.0	13.9		4.4	4.3		44.9	44.7	59以上	231	220		46	
※45-D13	良		14.0	13.9		4.4	4.3		44.8	44.7	79以上	231	219		46	
50-3.2	良		10.0	9.9		4.0	3.9		49.3	49.1	35以上	248	236		49	
50-4	良		10.0	9.9		3.9	3.9		49.3	49.1	40以上	246	239		49	
50-5	良		10.0	9.9		4.0	3.9		49.3	49.1	49以上	256	246		49	
50-6/D6	良		10.0	9.9		4.0	3.9		49.2	49.1	54以上	256	243		49	
50-D10	良		12.1	12.0		3.9	3.9		49.3	49.2	59以上	290	277		46	
50-D13	良		12.1	12.0		4.0	3.9		49.2	49.1	79以上	285	274		44	
55-3.2	良		12.0	11.9		4.0	3.9		54.6	54.4	35以上	268	257		48	
55-4	良		12.0	11.9		4.1	4.0		54.6	54.4	40以上	271	262		48	
55-5	良		12.0	11.9		4.0	4.0		54.7	54.5	49以上	275	261		47	
55-D6	良		12.0	11.9		4.2	4.0		54.6	54.5	54以上	279	267		47	
55-D10	良		13.3	13.2		4.4	4.3		54.5	54.2	59以上	393	381		50	
55-D13	良		13.4	13.3		4.4	4.3		54.4	54.2	79以上	399	387		49	

令和 8 年 2 月度

項目 種類	外観及び形状	寸 法 及 び 許 容 差 mm									圧縮強さ N			開孔率 %		
		a			b			d			JIS規格値		測定値		a	
		JIS規格値	測定値		JIS規格値	測定値		JIS規格値	測定値							
			最大	最小		最大	最小		最大	最小	最大	最小	JIS規格値	測定値		
60-3.2	良	9.0以上	12.0	11.9	3.0以上	4.4	4.4	±2.5	59.9	59.7	35以上	193	181	35以上	53	
60-4	良		12.0	11.9		4.5	4.4		59.9	59.7	40以上	189	178		53	
60-5	良		12.0	11.9		4.5	4.4		59.9	59.7	49以上	195	182		53	
60-6/D6	良		12.0	11.9		4.5	4.5		59.9	59.7	54以上	190	180		53	
60-D10	良		14.0	13.9		4.5	4.4		59.8	59.6	59以上	254	245		46	
60-D13	良		14.0	13.9		4.5	4.4		59.8	59.7	79以上	256	245		45	
65-4	良		15.0	14.9		4.5	4.4		64.8	64.6	40以上	223	213		50	
65-5	良		15.0	14.9		4.5	4.4		64.8	64.7	49以上	229	218		50	
65-D6	良		15.0	14.9		4.5	4.4		64.7	64.6	54以上	234	221		50	
65-D10	良		15.0	14.9		4.4	4.4		64.7	64.6	59以上	278	265		49	
65-D13	良		15.0	14.9		4.5	4.4		64.7	64.6	79以上	285	268		48	
70-4	良		15.0	14.9		4.9	4.8		69.5	69.3	40以上	205	191		51	
70-5	良		15.0	14.7		5.0	4.9		69.5	69.4	49以上	210	197		51	
70-6/D6	良		15.0	14.9		4.9	4.8		69.6	69.3	54以上	218	203		50	
70-D10	良		15.0	14.9		4.9	4.8		69.5	69.3	59以上	241	231		49	
70-D13	良		15.0	14.9		4.9	4.8		69.5	69.3	79以上	239	229		49	
75-4	良		21.2	21.1		3.4	3.3		74.3	74.1	40以上	334	321		44	
75-5	良		21.2	21.1		3.3	3.2		74.4	74.1	49以上	336	321		44	
75-D6	良		21.3	21.2		3.4	3.3		74.3	74.1	54以上	336	324		44	
75-D10	良		21.3	21.2		3.4	3.3		74.5	74.2	59以上	342	329		43	
75-D13	良	21.3	21.1	3.4	3.3	74.5	74.2	79以上	337	326	43					
80-4	良	16.1	16.0	4.9	4.8	79.6	79.4	40以上	208	194	43					
80-5	良	16.0	15.9	5.0	4.9	79.8	79.6	49以上	214	202	43					
80-6/D6	良	16.1	16.0	4.9	4.8	79.7	79.5	54以上	220	205	43					
80-D10	良	16.1	16.0	4.9	4.9	79.7	79.6	59以上	231	219	44					
80-D13	良	16.1	16.0	4.9	4.8	79.7	79.5	79以上	234	221	43					
85-4	良	21.5	21.4	3.5	3.4	84.1	83.9	40以上	303	286	47					
85-5	良	21.5	21.4	3.5	3.4	84.2	83.9	49以上	305	291	47					
85-D6	良	21.6	21.5	3.6	3.5	84.1	84.0	54以上	301	287	47					
85-D10	良	21.6	21.5	3.6	3.5	84.6	84.4	59以上	312	295	46					
85-D13	良	21.6	21.5	3.6	3.5	84.6	84.5	79以上	304	294	46					
90-4	良	17.0	16.9	5.8	5.8	89.8	89.5	40以上	198	185	55					
90-5	良	17.0	16.9	5.8	5.8	89.7	89.6	49以上	193	181	54					
90-6/D6	良	16.9	16.9	5.8	5.7	89.7	89.6	54以上	197	181	54					
90-D10	良	17.0	16.9	5.8	5.7	89.7	89.5	59以上	206	191	54					
90-D13	良	17.0	16.9	5.8	5.7	89.7	89.5	79以上	200	184	53					
●95-4	良	◆9.0以上	23.7	23.5	◆3.0以上	3.8	3.7	◆±2.5	94.7	94.4	40以上	279	266	◆35以上	49	
●95-5	良		23.6	23.5		3.8	3.7		94.7	94.6	49以上	284	268		49	
●95-D6	良		23.6	23.5		3.8	3.7		94.7	94.5	54以上	281	263		49	
●95-D10	良		23.6	23.5		3.8	3.7		94.7	94.6	59以上	284	269		49	
●95-D13	良		23.7	23.5		3.7	3.6		94.8	94.7	79以上	280	266		49	
●100-4	良		18.0	17.9		7.0	6.9		99.5	99.3	40以上	262	248		55	
●100-5	良		18.1	17.9		7.0	6.9		99.4	99.2	49以上	262	246		55	
●100-6/D6	良		18.0	17.9		7.0	6.9		99.4	99.3	54以上	258	243		55	
●100-D10	良		18.0	17.9		7.0	6.9		99.5	99.2	59以上	266	251		55	
●100-D13	良		18.0	17.9		7.0	6.9		99.4	99.2	79以上	268	248		54	

令和 8 年 2 月度

項目 種類	外観及び形状	寸法及び許容差 mm								圧縮強さ N			開孔率 %						
		a			b			d			JIS規格値		a						
		JIS規格値	測定値		JIS規格値	測定値		JIS規格値	測定値				JIS規格値	測定値					
			最大	最小		最大	最小		最大	最小	最大	最小							
重50-D6	良	8.0以上	15.9	15.8	2.5以上	5.0	4.9	±2.0	49.3	49.2	54以上	485	471	35以上	43				
重50-D10	良		16.0	15.9		5.0	4.9		49.3	49.1	59以上	483	468		42				
重50-D13	良		16.0	15.8		5.0	4.8		49.3	49.2	79以上	479	463		40				
重50-D16	良		15.9	15.9		5.0	4.9		49.3	49.1	98以上	490	475		38				
重50-D19	良		15.9	15.8		4.9	4.8		49.4	49.3	118以上	484	469		35				
重60-D6	良	9.0以上	18.0	17.9	3.0以上	6.1	6.0	±2.5	59.3	59.2	54以上	683	666		43				
重60-D10	良		18.0	17.8		6.1	6.0		59.4	59.3	59以上	689	673		42				
重60-D13	良		17.9	17.8		6.1	6.0		59.4	59.2	79以上	681	664		41				
重60-D16	良		17.9	17.8		6.1	6.0		59.3	59.0	98以上	780	766		41				
重60-D19	良		17.9	17.8		6.1	6.0		59.3	59.1	118以上	779	762		40				
重65-D16	良		17.9	17.8		6.0	5.9		64.3	64.2	98以上	517	500		44				
重65-D19	良		17.9	17.7		6.0	5.9		64.3	64.1	118以上	509	489		40				
重70-D6	良		19.0	18.9		7.1	7.0		69.3	69.1	54以上	809	786		45				
重70-D10	良		19.0	18.9		7.0	6.9		69.3	69.1	59以上	817	786		44				
重70-D13	良		19.0	18.9		7.0	6.9		69.3	69.1	79以上	807	783		43				
重70-D16	良		19.0	18.9		6.9	6.8		69.3	69.2	98以上	895	878		44				
重70-D19	良		19.0	18.9		6.9	6.8		69.3	69.1	118以上	923	905		43				
重80-D6	良		19.8	19.8		7.5	7.4		79.6	79.4	54以上	791	775		48				
重80-D10	良		19.9	19.7		7.5	7.4		79.7	79.5	59以上	785	770		47				
重80-D13	良		19.9	19.8		7.5	7.4		79.6	79.4	79以上	795	782		47				
重80-D16	良		19.9	19.8		7.5	7.4		79.7	79.4	98以上	820	795		46				
重80-D19	良		19.9	19.8		7.5	7.4		79.7	79.5	118以上	825	808		45				
重90-D6	良		20.9	20.8		8.2	8.1		89.7	89.5	54以上	953	940		48				
重90-D10	良		20.9	20.8		8.2	8.1		89.8	89.6	59以上	952	941		47				
重90-D13	良		20.9	20.9		8.1	8.0		89.8	89.6	79以上	981	968		46				
重90-D16	良		20.9	20.8		8.1	8.1		89.8	89.6	98以上	1038	1027		46				
重90-D19	良		20.9	20.8		8.2	8.1		89.9	89.6	118以上	1071	1060		46				
●重100-D6	良	◆9.0以上	20.9	20.8	◆3.0以上	7.9	7.8	◆±2.5	99.1	98.9	54以上	646	630	◆35以上	52				
●重100-D10	良		20.9	20.8		7.9	7.8		99.1	98.9	59以上	675	656		52				
●重100-D13	良		20.9	20.8		7.9	7.8		99.1	98.9	79以上	671	652		51				
●重100-D16	良		21.0	20.9		7.9	7.8		99.1	98.9	98以上	637	618		50				
●重100-D19	良		21.0	20.9		8.0	7.9		99.1	98.8	118以上	626	615		48				
●重100-D22	良		21.0	20.9		8.0	7.9		99.1	99.0	◆118以上	554	537		50				
●重100-D25	良		21.0	20.9		7.9	7.9		99.0	98.9		560	545		49				
●重110-D6	良		20.9	20.7		7.9	7.8		109.0	108.7	54以上	625	615		54				
●重110-D10	良		20.9	20.7		7.9	7.8		108.9	108.7	59以上	643	625		53				
●重110-D13	良		20.9	20.8		7.9	7.8		109.2	109.0	79以上	589	567		53				
●重110-D16	良		20.9	20.8		7.8	7.8		109.3	109.2	98以上	635	621		52				
●重110-D19	良		21.0	20.9		7.9	7.8		109.4	109.2	118以上	551	534		52				
●重110-D22	良		20.9	20.8		7.8	7.8		109.2	109.1	◆118以上	550	533		52				
●重110-D25	良		20.9	20.9		7.9	7.8		109.3	109.1		610	587		51				
●重120-D6	良		20.9	20.7		7.9	7.8		118.9	118.6	54以上	503	486		57				
●重120-D10	良		20.9	20.8		7.9	7.8		119.1	118.9	59以上	517	496		57				
●重120-D13	良		20.9	20.8		7.9	7.8		119.1	118.7	79以上	508	488		56				
●重120-D16	良		20.9	20.8		7.9	7.8		119.1	118.8	98以上	513	493		55				
●重120-D19	良		20.9	20.8		7.9	7.8		119.0	118.7	118以上	515	497		55				
●重120-D22	良		20.9	20.8		7.9	7.8		119.0	118.8	◆118以上	506	490		55				
●重120-D25	良		20.8	20.8		7.8	7.8		118.9	118.8		505	483		55				

令和 8 年 2 月度

項目 種類	外観 及び 形状	寸 法 及 び 許 容 差 mm									圧縮強さ N			開孔率 %				
		a			b			d			JIS 規格値	測定値		JIS 規格値	測定値			
		JIS 規格値	測定値		JIS 規格値	測定値		JIS 規格値	測定値									
			最大	最小		最大	最小		最大	最小								
●重130-D10	良	◆9.0以上	23.8	23.6	◆3.0以上	8.9	8.8	◆±2.5	128.6	128.4	59以上	532	521	◆35以上	56			
●重130-D13	良		23.8	23.7			8.9		8.8	128.5	128.3	79以上	534		522	56		
●重130-D16	良		24.0	23.9			8.9		8.8	128.8	128.7	98以上	400		381	55		
●重130-D19	良		23.9	23.8			8.9		8.9	128.9	128.8	118以上	396		377	55		
●重130-D22	良		23.8	23.7			8.9		8.8	128.8	128.7	◆118以上	415		403	55		
●重130-D25	良		23.9	23.7			8.8		8.8	128.9	128.8		423		411	54		
●重140-D10	良		23.8	23.6			8.9		8.8	138.3	138.1	59以上	469		454	59		
●重140-D13	良		23.8	23.6			8.9		8.8	138.3	138.2	79以上	463		451	58		
●重140-D16	良		23.9	23.9			8.9		8.8	138.5	138.4	98以上	353		338	58		
●重140-D19	良		23.9	23.8			8.9		8.8	138.4	138.3	118以上	345		334	58		
●重140-D22	良		23.9	23.8			8.9		8.9	138.9	138.7	◆118以上	352		336	58		
●重140-D25	良		23.9	23.9			9.0		8.8	138.9	138.8		359		343	57		
●重150-D10	良		25.9	25.8			9.0		8.9	149.5	149.3	59以上	310		294	61		
●重150-D13	良		25.9	25.7			9.0		8.9	149.5	149.2	79以上	316		302	61		
●重150-D16	良		25.9	25.7			9.0		8.9	149.5	149.3	98以上	323		307	60		
●重150-D19	良		25.9	25.8			9.0		8.9	149.8	149.6	118以上	341		327	60		
●重150-D22	良		25.9	25.8			9.0		8.9	149.4	149.2	◆118以上	430		418	60		
●重150-D25	良		26.0	25.8			8.9		8.9	149.4	149.3		432		421	60		
●重160-D10	良		25.9	25.7			10.0		9.9	158.6	158.3	59以上	331		318	60		
●重160-D13	良		25.9	25.7			10.0		9.9	158.6	158.3	79以上	331		321	60		
●重160-D16	良		25.9	25.8			10.0		10.0	159.1	159.0	98以上	418		395	60		
●重160-D19	良		26.0	25.9			10.0		9.9	159.3	159.2	118以上	413		392	60		
●重160-D22	良		25.9	25.8			10.0		10.0	159.3	159.1	◆118以上	428		411	60		
●重160-D25	良		26.0	25.9			10.0		9.9	159.4	159.2		417		404	60		
ヒ 40-5	良		8.0以上	21.1		21.0	2.5以上		4.8	4.7	±2.0	39.4	39.3		49以上	447	434	35以上
ヒ 40-6	良	21.6		21.5		5.0		4.8	39.4	39.3		54以上	453	441	43			
ハ 40-9	良	21.5		21.3		4.8		4.7	39.4	39.2		59以上	453	440	43			
ヒ 50-5	良	24.1		24.0		5.8		5.7	49.2	49.0		49以上	478	461	44			
ヒ 50-6	良	24.3		24.2		5.9		5.9	49.4	49.3		54以上	473	458	44			
ハ 50-9	良	24.5		24.4		5.9		5.8	49.7	49.6		59以上	474	457	44			
ハ 50-13	良	24.4		24.3		6.0		5.9	49.6	49.5		79以上	466	452	44			
ヒ 60-6	良	9.0以上	24.3	24.2	3.0以上	6.1	6.0	±2.5	59.4	59.3	54以上	588	574		46			
ハ 60-9	良		24.5	24.4			6.1		5.9	59.0	58.9	59以上	585	567	46			
ハ 60-13	良		24.4	24.4			5.9		5.7	58.9	58.7	79以上	580	567	46			
40-D6	良	8.0以上	9.1	9.0	2.5以上	3.0	3.0	±2.0	39.5	39.4	54以上	160	150		45			
45-D6	良		10.1	10.0			3.5		3.5	45.1		45.0	187	172	47			
50-D6	良		10.0	9.9			4.0		3.9	49.3		49.0	256	244	49			
60-D6	良		9.0以上	12.0		11.9	3.0以上		4.4	4.3		±2.5	59.8	59.6	189	175	53	
70-D6	良			15.1		15.0				4.9			4.8	69.6	69.4	205	189	50
80-D6	良			16.1		16.0				4.9			4.8	79.7	79.6	209	192	43
90-D6	良			17.0		16.9				5.8			5.7	89.7	89.5	196	184	54
●50-D5	良	8.0以上	10.1	10.0	2.5以上	4.0	3.9	±2.0	49.2	49.0	◆49以上	254	242		49			
●60-D5	良	9.0以上	12.0	11.9	3.0以上	4.4	4.3	±2.5	59.8	59.6		185	172	53				
●80-D5	良		16.1	16.0		4.9	4.9		79.6	79.4		212	197	43				

備考 1. 本表は、JIS A 5390（鉄筋コンクリート製品用プラスチックスペーサ）の規定に準拠したものである。

2. 測定値の小数点2位以下は切り捨てる。

なお圧縮強さ及び開孔率の測定値は、小数点以下は切り捨てる。

3. 寸法及び外径の許容差は、前月度の測定値とする。

4. 圧縮強さ及び開孔率は、年1回の測定値とする。

5. 重は重圧、ヒはヒューム管、パはパイル、※は旧型、●はJIS規格外品（◆は自社規格値）。